

Dispersion Adhesive DK

Adhesive composition for low absorbency substrates



Description	Adhesive composition for low absorbency substrates	
Features	For bonding EPS insulation boards and mineral fibre lamellas to weakly absorbent substrates	
Application	Cementless adhesive for EPS insulation boards on slightly absorbent substrates such as chipboard, hardboard, OSB boards and cement-bonded boards. Also suitable for flat mineral substrates such as concrete, aerated concrete, plaster and masonry. All substrates must be dry, load-bearing, clean and free of adhesion-reducing residues.	
Consumption	Approx. 2.5-3.5 kg/m ²	
Technical data	Classification	External plaster according to EN 15824 with organic binders
	Density	approx. 1.7 kg/m ²
	Adhesion	>= 0.3 MPas according to EN 1542
	Water vapour permeability S _d	Class V ₂ (medium) according to EN ISO 7783-2
	Water absorption	Class W ₃ (low) according to EN 1062-3
Processing	<p>Material can be processed after short stirring with a slow-running agitator. If necessary, adjust consistency with a little water. Apply with a steel trowel and apply the required amount with a 10 mm toothed trowel. Apply panels by pushing and pressing lightly. Depending on the weather, a service life of at least 3 days is required.</p> <p>Clean tools immediately after use with water. To avoid build-up and structural defects, work through quickly wet in wet and use sufficient manpower for larger surfaces. Only use material with the same batch number on contiguous surfaces or Mix materials with different batch numbers beforehand. Carefully cover adjacent surfaces. Wash off splashes immediately with plenty of water. Do not use with air and Building temperatures below +5°C, as well as direct sunlight, draughts or expected night frosts.</p> <p>Particular attention should be paid: VOB, Part C, DIN 18363, Sections 2 and 3, as well as the BFS bulletins for the relevant working areas.</p> <p>WE special setting: Fast surface drying leads to early rain resistance. Alkaline substrates prevent the drying process from accelerating and can lead to colour deviations. Drying is physical and therefore strongly dependent on temperature, humidity and air movement. The relative humidity must not exceed 95 %. The lowest processing temperature for air and building body temperature is +1°C. It is recommended to take protective measures (rain protection) on the facade to be on the safe side.</p>	
Surface coating	-	
Form of Delivery	25 kg bucket (24 buckets/pallet)	
Storage	Store tightly closed, cool and frost-free.	
Reference	Protect eyes and skin. Giscode: M-DF02	
Consulting service	The information given in this data sheet is only general guidelines. Should technical questions arise in a specific application, please contact our sales office.	

Dispersion Adhesive DK

Adhesive composition for low absorbency substrates

Optics

-

Colour

Natural white

Options



WE - Early rain resistance for temperatures from +1°C to 10°C

All information in this publication is based on experience, tests and trials. A guarantee for the general validity of individual Data and statements are excluded with regard to different processing and construction site conditions. The generally recognised and technical rules of construction engineering as well as the applicable standards and guidelines must be observed. Previous editions are invalid with the publication of this publication. We reserve the right to make changes within the scope of further product and application developments. Please refer to our Internet pages for the latest information. For all business transactions, our current Terms and conditions of sale and delivery.

HUMA FARBEN GmbH

Ziegelfeldstraße 66 D-73563 Mögglingen
 Fon +49.(0)7174.89899-0
 Fax +49.(0)7174.89899-18
www.huma-farben.de info@huma-farben.de