

SuperDecker ELF

Solvent-free dull matt and highly opaque interior paint (wet abrasion class 3 according to EN 13300)



Description	Solvent-free dull matt and highly opaque interior paint (wet abrasion class 3 according to EN 13300)
Features	Solvent- and plasticizer-free, highly opaque, extra matt and very easy to repair
Application	<p>New substrates: Remove dirt and clean surfaces. Remove any sintered skin.</p> <p>Old substrates: Thoroughly clean surfaces wet or dry. Loose paint parts, as well as unstable old paintwork and remove and re-clean coatings (mechanical or suitable paint strippers).</p> <p>Plaster of mortar groups PG II + III: Coat solid, normally absorbent substrates without pretreatment. Prime coarsely porous, sandy and highly absorbent plasters with Deep Primer LF.</p> <p>Gypsum and finished plasters of mortar groups PG IV + V: Sand and dust any existing sinter layers. Prime with Deep Primer LF.</p> <p>Gypsum building boards: For absorbent substrates, prime with Deep Primer LF.</p> <p>Plasterboard: Prime with Deep Primer LF.</p> <p>Concrete: Remove impurities and prime with Tiefgrund LF.</p> <p>Porous concrete: Priming with Tiefgrund LF and smoothing filler.</p> <p>Brick exposed masonry: Clean and remove dust, then prime with Tiefgrund LF.</p> <p>Wood, fibreboard, chipboard and plywood boards: Prime with Deep Primer LF.</p> <p>Load-bearing coatings: Repair matt, weakly absorbent coatings directly. Roughen glossy surfaces and lacquer coatings. Completely remove non-bearing coatings and prime substrate with Deep Primer LF.</p> <p>Old lime and mineral paints: Wash thoroughly and prime with Deep Primer LF.</p> <p>Glue paints: Wash thoroughly.</p> <p>Wallpaper (surfaces with water, nicotine or soot stains): Wash and prime with insulating primer.</p>
Consumption	approx. 0.15-0.2 l/m ² per coat

SuperDecker ELF

Solvent-free dull matt and highly opaque interior paint (wet abrasion class 3 according to EN 13300)

Technical data	Composition Polymer dispersion, titanium dioxide, mineral and silicate Fillers, calcium carbonate, additives, water. Density approx. 1.5 g/cm ² Wet abrasion resistance class 3 according to DIN EN 13300 Opacity class 2 according to DIN EN 13300 Gloss Dull matt according to DIN EN 13300	
Processing	<p>Material is ready for processing after short stirring. If two coats are applied, the first coat can be diluted with 5-10% clean water, depending on the absorbency of the substrate. Application by roller, brush or spray gun. Apply evenly and without any build-up.</p> <p>Tool cleaning after use with water. Carefully cover adjacent surfaces, in particular glass, plastics, natural stone, metals or similar. Wash off splashes immediately with plenty of water.</p> <p>Only use material with the same batch number or the same production date on continuous surfaces. Mix material with different numbers before processing.</p> <p>Do not process at air and building temperatures below +5°C. Can be recoated after approx. 8 hours (+20°C, 65% RLF).</p>	
Surface coating	-	
Form of Delivery	15,0 l/bucket (24 buckets/pallet) 10,0 l/pail (40 pails/pallet)	5,0 l/bucket (64 buckets/pallet) 2,5 l/pail (80 pails/pallet)
Storage	Store buckets tightly closed, cool and frost-free.	
Reference	Protect eyes and skin. Giscode: M-DF01	
Consulting service	The information given in this data sheet is only general guidelines. Should technical questions arise in a specific application, please contact our sales office.	
Optics	Matt	
Colour	Weiß oder getönt	
Options	-	

All information in this publication is based on experience, tests and trials. A guarantee for the general validity of individual Data and statements are excluded with regard to different processing and construction site conditions. The generally recognised and technical rules of construction engineering as well as the applicable standards and guidelines must be observed. Previous editions are invalid with the publication of this publication. We reserve the right to make changes within the scope of further product and application developments. Please refer to our Internet pages for the latest information. For all business transactions, our current Terms and conditions of sale and delivery.

HUMA FARBEN GmbH
 Ziegelfeldstraße 66 D-73563 Mögglingen
 Fon +49.(0)7174.89899-0
 Fax +49.(0)7174.89899-18
 www.huma-farben.de info@huma-farben.de